



# H66 2K UHS PRESTIGE

## Ultra high solid 2K acrylic clear coat

### A) DESCRIPTION AND FIELDS OF APPLICATION:

Two-pack, ultra high solid acrylic clear coat complying with VOC standard limits.

Its main features include: ease of application, extremely transparent effect, excellent spreading, high gloss and fast drying time. It is especially suitable for bodyshop repair work using waterbourne base coats as it cuts effects caused by the absorption of these latter.

Standard 2004/42 states that the maximum VOC rating for this product in subcategory IIB(d) is 420 g/l. The VOC for this ready-to-use product is below 420g/l.

### B) TECHNICAL DATA:

Composition	Hydroxylated acrylic resins
Specific weight	0,98 ± 0,03
Available colours	Neutral clear
Safety data	Refer to the safety sheet

### C) SURFACE PREPARATION :



- \* Solvent basecoat
- \* waterbourne basecoat

### D) CAUTIONS:

- \* Two component acrylic paints are affected by moisture.
- \* Comply with the application ratios
- \* Do not use the product at temperatures below 5°C.
- \* Keep in a cool, dry place.

**E) PROCESSING:****3:1 C65/C66 UHS Hardener potlife > 60' at 20°C.****Do not Dilute  
18-19" CF 4 at 20°C.****1,3-1,4 mm 3,5-4 bar  
1+1/2 = 50-60 micron****1,4-1,5 mm 3,5-5 bar  
1+1/2 = 50-60 micron****10'-15' drying depending on temperature****8 h at 20°C.  
30' at 60°C.****12' at 1 mt.****F) TOOLS CLEANING:**

With thinner for polyurethane products.

**G) RECOATING :**

Technical indications and advices are based on our own experiences. We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained